

Williamsburg®

ARTIST OIL COLORS

OIL BY VOLUME

♠ (low)

♠♠ (moderate)

♠♠♠ (medium)

♠♠♠♠ (high)

Colors are in order from lowest to highest % oil content by volume.

DAYS TO DRY

DRY TIME

1-2 **F** (fast)

2-7 **M** (medium)

5-14 **S** (slow)

10-21 **VS** (very slow)

COLOR	OIL BY VOLUME	DRY TIME
Cobalt Yellow	♠	F
Italian Rosso Veneto	♠	F
French Rouge Indien	♠	M
Italian Pompeii Red	♠	S
Italian Lemon Ochre	♠	M
French Raw Umber	♠	M
Davy's Grey Deep	♠	M
Nickel Yellow	♠	M
French Ardoise Grey	♠	M
Manganese Violet	♠	F
Italian Yellow Ochre	♠	F
Cobalt Teal Bluish	♠	M
Italian Green Ochre	♠	F
Cobalt Violet Light	♠	M
Spanish Earth	♠	F
French Terre Verte	♠	M
Ultramarine Pink	♠	S
SF Porcelain White	♠	M
Brown Ochre	♠	F
King's Blue	♠	F
Italian Pozzuoli Earth	♠	F
Chromium Oxide Green	♠	M
Cobalt Green	♠	M
Ultramarine Blue	♠	M
Cobalt Violet Deep	♠	M
Italian Orange Ochre	♠	M
SF Ultramarine Blue	♠	M
Cobalt Teal Greenish	♠	M
Ultramarine Violet	♠	S
Yellow Ochre Burnt	♠	F
Naples Yellow Italian	♠	M
Canton Rose	♠	M
SF Ultramarine Violet	♠	S
Cadmium Yellow Extra Deep	♠	M

Cadmium Lemon	♠	M
Cadmium Red Deep	♠	S
Titanium White	♠	F
Cadmium Yellow Light	♠	M
Neutral Gray N8	♠	F
SF Cobalt Violet Light	♠	M
Titanium-Zinc White	♠	M
Cadmium Red Light	♠	M
SF Ultramarine Pink	♠	S
Titan Buff	♠	M
Dianthus Pink	♠	M
SF Ultramarine Blue French	♠	M
French Yellow Ochre Deep	♠	S
Cadmium Red Vermilion	♠	S
Cobalt Turquoise Greenish	♠	F
Cadmium Yellow Medium	♠	M
Red Ochre	♠	M
Ultramarine Blue (French)	♠	M
French Raw Sienna	♠	M
SF French Ardoise Grey	♠	M
Brilliant Yellow Extra Pale	♠	M
Earth Green	♠♠	F
French Brown Ochre	♠♠	M
Brilliant Yellow Pale	♠♠	M
Cerulean Blue (Genuine)	♠♠	M
French Light Sienna	♠♠	M
Neutral Gray N4	♠♠	F
Unbleached Titanium	♠♠	F
Courbet Green	♠♠	F
Naples Yellow	♠♠	M
Payne's Grey	♠♠	M
Cobalt Turquoise Bluish	♠♠	F
Unbleached Titanium Pale	♠♠	F
Neutral Gray N6	♠♠	F
Cold Black	♠♠	M

Monseratt Orange	♠♠	M
SF Titanium White	♠♠	M
French Ochre Havane	♠♠	M
French Burnt Ochre	♠♠	M
Cadmium Purple	♠♠	S
Italian Black Roman Earth	♠♠	F
Zinc White	♠♠	VS
Jaune Brilliant	♠♠	F
Indigo	♠♠	F
Cerulean Blue French	♠♠	F
Naples Yellow Reddish	♠♠	M
Turkey Umber	♠♠	F
Italian Burnt Sienna	♠♠	M
Cadmium Red Purple	♠♠	S
Cadmium Red Medium	♠♠	M
Flake White	♠♠	M
Pyrrole Red	♠♠	M
Raw Sienna	♠♠	F
Sevres Blue	♠♠	M
Cadmium Yellow Deep	♠♠	M
Raw Umber	♠♠	F
Permanent Yellow Medium	♠♠	M
Brown Umber	♠♠	F
Mars Black	♠♠	M
Mars Red	♠♠	F
Cadmium Orange	♠♠	S
Yellow Ochre (Domestic)	♠♠	M
SF Italian Terra Verte	♠♠	M
Mars Violet	♠♠	M
SF Flake White	♠♠	M
Prussian Blue	♠♠	F
Burnt Sienna	♠♠	F
Cadmium Green Light	♠♠	F
Payne's Grey (Violet)	♠♠	F
Provence Violet Bluish	♠♠	S

continued >

Cyprus Orange	●●	F
Pyrrole Orange	●●	VS
Italian Raw Umber	●●	F
Italian Terra Rosa	●●	F
Italian Raw Sienna	●●	F
Italian Terra Verte	●●	F
Permanent Orange	●●	VS
Cinnabar Green Light	●●	M
Nickel Azo Yellow	●●●	M
Van Dyke Brown	●●●	M
Cobalt Blue Deep	●●●	F
Persian Rose	●●●	M
SF Cerulean Blue French	●●●	M
Ivory Black	●●●	M
Mars Red Light	●●●	F
Permanent Yellow Light	●●●	M
German Earth	●●●	F
Permanent Green Light	●●●	S
Permanent Lemon	●●●	M
Permanent Green	●●●	F
Cadmium Green	●●●	F
Quinacridone Gold Brown	●●●	M
Bohemian Green Earth	●●●	F
Indanthrone Blue	●●●	VS
Turquoise	●●●	S
Mars Orange	●●●	F
Burnt Umber	●●●	F
Phthalo Green Yellowish	●●●	F
Cobalt Blue	●●●	M
Permanent Red-Orange	●●●	M
Neutral Gray N2	●●●	F
Red Umber	●●●	F
Veronese Green	●●●	M
Mars Yellow Light	●●●	M
Bismuth Vanadate Yellow	●●●	M
Fanchon Red	●●●	VS

Provence Violet Reddish	●●●	M
French Burnt Umber	●●●	F
Viridian	●●●	F
Alizarin Crimson	●●●	VS
Permanent Yellow Deep	●●●	S
Dutch Brown (Transparent)	●●	F
Stil de Grain	●●	F
Carl's Crimson	●●	VS
Iridescent Bronze	●●●	S
Mars Yellow Deep	●●●	F
Graphite Grey	●●●	VS
Quinacridone Red	●●●	S
Italian Pink	●●●	M
Phthalo Blue	●●●	S
Perylene Crimson	●●●	M
Sap Green	●●●	F
Iridescent Pewter	●●●●	S
Quinacridone Violet	●●●●	S
Interference Green	●●●●	M
Egyptian Violet	●●●●	VS
Iridescent Silver	●●●●	M
Permanent Crimson	●●●●	M
Interference Blue	●●●●	M
Iridescent Pale Gold	●●●●	S
Transparent Yellow Iron Oxide	●●●●	F
Transparent Orange Iron Oxide	●●●●	F
Interference Red	●●●●	M
Quinacridone Magenta	●●●●	S
Brown Pink	●●●●	F
Interference Violet	●●●●	M
Olive Green	●●●●	F
Iridescent Pearl White	●●●●	M
Phthalo Turquoise	●●●●	F
Alizarin Yellow	●●●●	VS
Transparent Brown Iron Oxide	●●●●	F
Green Gold	●●●●	M

Iridescent Copper	●●●●	M
Phthalo Green	●●●●	F
Transparent Red Iron Oxide	●●●●	F
Alizarin Orange	●●●●	S
India Yellow	●●●●	VS
Lamp Black	●●●●	S
Lead Oil Ground (w/ TiO2)	●	F
Titanium Oil Ground	●	F
Extender Medium	●	M

OIL BY VOLUME	
● (low)	
●● (moderate)	
●●● (medium)	
●●●● (high)	

Colors are in order from lowest to highest % oil content by volume.

DAYS TO DRY		DRY TIME
1-2		F (fast)
2-7		M (medium)
5-14		S (slow)
10-21		VS (very slow)

Williamsburg
ARTIST OIL COLORS

williamsburg oils.com

©2023 Golden Artist Colors, Inc.

Williamsburg®

ARTIST OIL COLORS

DAYS TO DRY	DRY TIME
1-2	F (fast)
2-7	M (medium)
5-14	S (slow)
10-21	VS (very slow)

Colors are in order from fastest to slowest drying.

OIL BY VOLUME
♠ (low)
♠♠ (moderate)
♠♠♠ (medium)
♠♠♠♠ (high)

COLOR	OIL BY VOLUME	DRY TIME
Cobalt Yellow	♠	F
Italian Rosso Veneto	♠	F
Manganese Violet	♠	F
Italian Yellow Ochre	♠	F
Italian Green Ochre	♠	F
Spanish Earth	♠	F
Brown Ochre	♠	F
King's Blue	♠	F
Italian Pozzuoli Earth	♠	F
Yellow Ochre Burnt	♠	F
Titanium White	♠	F
Neutral Gray N8	♠	F
Cobalt Turquoise Greenish	♠	F
Earth Green	♠♠	F
Neutral Gray N4	♠♠	F
Unbleached Titanium	♠♠	F
Courbet Green	♠♠	F
Cobalt Turquoise Bluish	♠♠	F
Unbleached Titanium Pale	♠♠	F
Neutral Gray N6	♠♠	F
Italian Black Roman Earth	♠♠	F
Jaune Brilliant	♠♠	F
Indigo	♠♠	F
Cerulean Blue French	♠♠	F
Turkey Umber	♠♠	F
Raw Sienna	♠♠	F
Raw Umber	♠♠	F
Brown Umber	♠♠	F
Mars Red	♠♠	F
Prussian Blue	♠♠	F
Burnt Sienna	♠♠	F
Cadmium Green Light	♠♠	F
Payne's Grey (Violet)	♠♠	F
Cyprus Orange	♠♠	F

Italian Raw Umber	♠♠	F
Italian Terra Rosa	♠♠	F
Italian Raw Sienna	♠♠	F
Italian Terra Verte	♠♠	F
Cobalt Blue Deep	♠♠♠	F
Mars Red Light	♠♠♠	F
German Earth	♠♠♠	F
Permanent Green	♠♠♠	F
Cadmium Green	♠♠♠	F
Bohemian Green Earth	♠♠♠	F
Mars Orange	♠♠♠	F
Burnt Umber	♠♠♠	F
Phthalo Green Yellowish	♠♠♠	F
Neutral Gray N2	♠♠♠	F
Red Umber	♠♠♠	F
French Burnt Umber	♠♠♠	F
Viridian	♠♠♠	F
Dutch Brown (Transparent)	♠♠	F
Stil de Grain	♠♠	F
Mars Yellow Deep	♠♠♠	F
Sap Green	♠♠♠	F
Transparent Yellow Iron Oxide	♠♠♠♠	F
Transparent Orange Iron Oxide	♠♠♠♠	F
Brown Pink	♠♠♠♠	F
Olive Green	♠♠♠♠	F
Phthalo Turquoise	♠♠♠♠	F
Transparent Brown Iron Oxide	♠♠♠♠	F
Phthalo Green	♠♠♠♠	F
Transparent Red Iron Oxide	♠♠♠♠	F
French Rouge Indien	♠	M
Italian Lemon Ochre	♠	M
French Raw Umber	♠	M
Davy's Grey Deep	♠	M
Nickel Yellow	♠	M
French Ardoise Grey	♠	M

Cobalt Teal Bluish	♠	M
Cobalt Violet Light	♠	M
French Terre Verte	♠	M
SF Porcelain White	♠	M
Chromium Oxide Green	♠	M
Cobalt Green	♠	M
Ultramarine Blue	♠	M
Cobalt Violet Deep	♠	M
Italian Orange Ochre	♠	M
SF Ultramarine Blue	♠	M
Cobalt Teal Greenish	♠	M
Naples Yellow Italian	♠	M
Canton Rose	♠	M
Cadmium Yellow Extra Deep	♠	M
Cadmium Lemon	♠	M
Cadmium Yellow Light	♠	M
SF Cobalt Violet Light	♠	M
Titanium-Zinc White	♠	M
Cadmium Red Light	♠	M
Titan Buff	♠	M
Dianthus Pink	♠	M
SF Ultramarine Blue French	♠	M
Cadmium Yellow Medium	♠	M
Red Ochre	♠	M
Ultramarine Blue (French)	♠	M
French Raw Sienna	♠	M
SF French Ardoise Grey	♠	M
Brilliant Yellow Extra Pale	♠	M
French Brown Ochre	♠♠	M
Brilliant Yellow Pale	♠♠	M
Cerulean Blue (Genuine)	♠♠	M
French Light Sienna	♠♠	M
Naples Yellow	♠♠	M
Payne's Grey	♠♠	M
Cold Black	♠♠	M

continued >

Monserrat Orange	◆◆	M
SF Titanium White	◆◆	M
French Ochre Havane	◆◆	M
French Burnt Ochre	◆◆	M
Naples Yellow Reddish	◆◆	M
Italian Burnt Sienna	◆◆	M
Cadmium Red Medium	◆◆	M
Flake White	◆◆	M
Pyrrole Red	◆◆	M
Sevres Blue	◆◆	M
Cadmium Yellow Deep	◆◆	M
Permanent Yellow Medium	◆◆	M
Mars Black	◆◆	M
Yellow Ochre (Domestic)	◆◆	M
SF Italian Terra Verte	◆◆	M
Mars Violet	◆◆	M
SF Flake White	◆◆	M
Cinnabar Green Light	◆◆	M
Nickel Azo Yellow	◆◆◆	M
Van Dyke Brown	◆◆◆	M
Persian Rose	◆◆◆	M
SF Cerulean Blue French	◆◆◆	M
Ivory Black	◆◆◆	M
Permanent Yellow Light	◆◆◆	M
Permanent Lemon	◆◆◆	M
Quinacridone Gold Brown	◆◆◆	M
Cobalt Blue	◆◆◆	M
Permanent Red-Orange	◆◆◆	M
Veronese Green	◆◆◆	M
Mars Yellow Light	◆◆◆	M
Bismuth Vanadate Yellow	◆◆◆	M
Provence Violet Reddish	◆◆◆	M
Italian Pink	◆◆◆	M
Perylene Crimson	◆◆◆	M
Interference Green	◆◆◆◆	M
Iridescent Silver	◆◆◆◆	M

Permanent Crimson	◆◆◆◆	M
Interference Blue	◆◆◆◆	M
Interference Red	◆◆◆◆	M
Interference Violet	◆◆◆◆	M
Iridescent Pearl White	◆◆◆◆	M
Green Gold	◆◆◆◆	M
Iridescent Copper	◆◆◆◆	M
Ultramarine Pink	◆	S
Italian Pompeii Red	◆	S
Ultramarine Violet	◆	S
SF Ultramarine Violet	◆	S
Cadmium Red Deep	◆	S
SF Ultramarine Pink	◆	S
French Yellow Ochre Deep	◆	S
Cadmium Red Vermilion	◆	S
Cadmium Purple	◆◆	S
Cadmium Red Purple	◆◆	S
Cadmium Orange	◆◆	S
Provence Violet Bluish	◆◆	S
Permanent Green Light	◆◆◆	S
Turquoise	◆◆◆	S
Permanent Yellow Deep	◆◆◆	S
Iridescent Bronze	◆◆◆	S
Quinacridone Red	◆◆◆	S
Phthalo Blue	◆◆◆	S
Iridescent Pewter	◆◆◆◆	S
Quinacridone Violet	◆◆◆◆	S
Iridescent Pale Gold	◆◆◆◆	S
Quinacridone Magenta	◆◆◆◆	S
Alizarin Orange	◆◆◆◆	S
Lamp Black	◆◆◆◆	S
Zinc White	◆◆	VS
Pyrrole Orange	◆◆	VS
Permanent Orange	◆◆	VS
Indanthrone Blue	◆◆◆	VS
Fanchon Red	◆◆◆	VS

Alizarin Crimson	◆◆◆	VS
Carl's Crimson	◆◆◆	VS
Graphite Grey	◆◆◆	VS
Egyptian Violet	◆◆◆◆	VS
Alizarin Yellow	◆◆◆◆	VS
India Yellow	◆◆◆◆	VS
Lead Oil Ground (w/ TiO2)	◆	F
Titanium Oil Ground	◆	F
Extender Medium	◆	M

DAYS TO DRY	DRY TIME
1-2	F (fast)
2-7	M (medium)
5-14	S (slow)
10-21	VS (very slow)

Colors are in order from fastest to slowest drying.

OIL BY VOLUME
◆ (low)
◆◆ (moderate)
◆◆◆ (medium)
◆◆◆◆ (high)

Williamsburg
ARTIST OIL COLORS

williamsburg oils.com

©2023 Golden Artist Colors, Inc.